

QUALITY PARAMATERS

The Strataglass sheets are produced at 54" X 110". This is the nominal size before the two (2) inch edge allowance for occasional blemishes. The quality standard allows for blemishes within two (2) inches from outer edges. Sheets that have a blemish within two (2) inches PASS internal inspection. Sheets that have a blemish greater than two (2) inches from the edge FAIL internal inspection. The edge blemishes are an unavoidable result of the manufacturing process.

We thank you for trusting in Strataglass and will continue to innovate and invest in ways to improve quality and service. Our success can only be measured by your satisfaction and we appreciate your business.

1. Lamination

- a. Lamination shall be complete, creating an inseparable bond between layers, within a 50" x 108" area.

2. Clarity

- a. Clarity will meet or exceed ASTM standards listed on product specification sheets within a 50" x 108" area.

3. Visible Contaminants

- a. Visible, embedded contaminants (fibers, dust, dirt, etc.) shall not be greater than parameters on Strataglass' specialized TAPPI chart.

4. Non-removable, Air Inclusions and Air Distortion

- a. The product shall be free of these defects within a 50" x 108" area.
- b. These defects are common on the extreme edges of the sheet but shall not encroach on usability of the full, 50" x 108" usable area of each sheet.
- c. Many minor air inclusions can be easily removed by use of a heat gun or simply allowing the product to dwell in warm, sunny conditions. These are not considered to be 'Non-removable', per the criteria for this specification as they are remedied with little effort.

5. Sheet Thickness

- a. For Crystal Clear and Panorama product lines the sheet shall be +/- .006" of the advertised thickness within a 50" x 108" area.
- b. For Strataglass product lines the sheet shall be +/- .004" of advertised thickness within a 50" x 108" area.