



# Strataglass PanoramaFR

## PROPERTIES REPORT

PROPERTY	TEST METHOD	TEST RESULTS	
Thickness (Mil)		20	30
Width (In.)		54 x 110	
Tensile Strength (Lbs./In)	ATM D6693	4400	4126
Light Transmittance	ASTM D1003	90.6%	89%
Haze	ASTM D1003	1.0%	1.2%
Hydroburst	ASTM D751/A	150 PSI	230 PSI
Dimensional Stability	ASTM D1204	<1.4% Change	<2% Change
UV Blocking	HERC PE-P-3	>98% UVA	>98% UVA
Clarity	ASTM D1003	99.7%	99%
Life Expectancy		5 Years (Care & Exposure Dependent)	
Flame Resistance	CSFM Reg. Title 19, NFPA 701 ASTM E 84 Class A	Pass	

The information contained in this report is believed to be reliable. It is offered in good faith and intended for use as a general guide. Herculite makes no guarantee of results and assumes no obligation or liability whatsoever in connection with the possible use of this information. This report, including any statements concerning the possible use of our products, is not a license to operate under, or intended to suggest infringement of any existing patents.

Strataglass® is a registered trademark of Strataglass LLC, a subsidiary of Herculite Products, Inc., Emigsville, PA

STRATAGLASS LLC  
 800.581.5801  
[www.strataglass.com](http://www.strataglass.com)